

# **Confidential Report**

Our Ref: 25/11166C/04/22







Wira House, West Park Ring Road, Leeds, LS16 6QL, UK. Telephone: +44 (0) 113 259 1999

Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 16 May 2022

Our Ref: 25/11166C/04/22

Your Ref: ---

Page: 1 of 6

Client:	Jacaranda Carpe	tc
Client:	Jacaranua Carpe	.us

1 Cockerel Rise Magnetic Park Desborough Northamptonshire NN14 2WE

Job Title:	Fire Classification of One Sample of Carpet

Clients Order Ref: ---

Date of Receipt: 22 April 2022

Description of Sample: One sample of carpet, referenced; Babri.

Work Requested: We were asked to make the following test(s):

BS EN 13501-1 (loose laid)

- \* subcontracted test, UKAS accredited
- \*\* subcontracted test, EN ISO/IEC 17025 accredited
- \*\*\* not UKAS accredited



Note: This report relates only to the samples submitted and as described in the report.



Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk Website: www.bttg.co.uk

Date: 16 May 2022

Our Ref: 25/11166C/04/22 Your Ref: ---

Page: 2 of 6

Client: Jacaranda Carpets

FIRE TESTS ACCORDING TO BS EN ISO 11925-2:2020

Reaction to fire tests for building products – Part 2:

Ignitability when subjected to direct impingement of flame

Date of Test: 11/05/2022

#### **Conditioning**

Test specimens and filter paper conditioned as described in BS EN 13238:2010.

#### **Procedure**

The sample was tested in accordance with BS EN ISO 11925-2:2020.

Three specimens from each direction were tested in accordance with the above standard. Specified filter paper was placed beneath the specimen holder and replaced between tests.

The specimens were mounted vertically in the specimen holder so that one end and both sides were enclosed with the exposed end 30mm from the end of the frame. The burner was inclined at an angle of 45°. The flame height was set at 20 mm with the flame impinging on the specimen for 15 seconds on the centre line, 40 mm above the bottom edge.

A marker was placed 150 mm above the upper end of the burner and the time recorded when the flame tip reached the marker, if applicable. The following parameters were also recorded:-

- 1. If ignition occurs
- 2. Presence of flaming debris, if applicable
- 3. Ignition of the filter paper, if applicable

#### **Duration of test**

For a flame application time of 15 seconds, the total test duration is 20 seconds after application of the flame.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 16 May 2022

Our Ref: 25/11166C/04/22 Your Ref:

> Page: 3 of 6

Client: **Jacaranda Carpets** 

#### **Classification Criteria**

The samples were classified according to BS EN 13501-1:2018 Fire classification of Construction Products and Building Elements: Part 1 - Classification using Test Data from Reaction to Fire Tests, Table 1 - Classes of reaction to fire performance for construction products excluding floorings.

Flaming Classification			
Classification Criteria (mean values)			
E <sub>FL</sub>	Fs ≤ 150mm within 20 seconds		
F <sub>FL</sub>	Fails Class E <sub>FL</sub>		

Flaming droplets / particles classification			
Classification Criteria			
No classification	Pass		
d2	Fail (Ignition of paper)		

#### **Results**

Specimen			Tip of flame reaches 150mm		Flaming droplets	
		Ignition	Voc er Ne	Time taken (a)	Vac an Na	Ignition of
		(Yes or No)	Yes or No	Time taken (s)	Yes or No	Filter paper (Yes or No)
						•
Machine	1	Yes	No	No	No	No
Direction	2	Yes	No	No	No	No
Direction	3	Yes	No	No	No	No
Across	1	Yes	No	No	No	No
Machine	2	Yes	No	No	No	No
Direction	3	Yes	No	No	No	No

#### Note

The specimens of floor covering were tested loose laid over a 6mm fibre cement board, as defined in BS EN 13238:2010.

The substrate used was a fibre cement board (ISO 390) with a thickness of (6±1)mm and a density of (1,800±200) Kg/m<sup>3</sup> representing the standard substrate of Class A1fl or A2fl.

Note: Test BS EN ISO 11925-2:2020 is accredited under our flexible scope policy.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 16 May 2022

Our Ref: 25/11166C/04/22 Your Ref:

> Page: 4 of 6

Client: **Jacaranda Carpets** 

#### FIRE TESTS ACCORDING TO BS EN ISO 9239-1:2010

Reaction to fire tests for Floorings - Part 1: Determination of the burning behaviour using a radiant heat source (ISO 9239-1:2010)

Date of Test: 11/05/2022

#### **Conditioning**

The specimens were conditioned in accordance with BS EN 13238:2010. The substrate used was a fibre cement board (ISO 390) with a thickness of (6±1)mm and a density of (1,800±200) Kg/m³ representing the standard substrate of Class A1fl or A2fl.

#### **Procedure**

The test was carried out in accordance with BS EN ISO 9239-1:2010. The sponsor sampled and cut the specimens to the dimensions stated.

Specimens were individually placed in the combustion chamber and allowed to preheat for two minutes under a radiant panel, which gives an imposed radiant flux ranging from approximately 11.0 kW/m<sup>2</sup> to 1.0 kW/m<sup>2</sup> along the specimen.

The pilot flame used was the line burner as described and was applied to the surface of the specimen for 10 minutes and then removed.

The flame front was measured at the end of the test or at 30 minutes if applicable.

Test termination was considered to be when the flame front self extinguished or at 30 minutes, which ever is the sooner.

The heat flux from the panel incident on the specimen when self extinguished or at 30 minutes (critical heat flux CHF or HF-30) was calculated from a prior calibration.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 16 May 2022

Our Ref: 25/11166C/04/22 Your Ref:

> Page: 5 of 6

**Client: Jacaranda Carpets** 

#### **Classification Criteria**

The samples were classified according to BS EN 13501-1:2018 - Fire classification of Construction Products and Building Elements: Part 1: Classification using Test Data from Reaction to Fire Tests.

For floorings, including their surface coverings the classes are:

Classification	Classification Criteria (mean values) (kW/m²)				
Bfl	8.0				
Cfl	4.5				
Dfl	3.0				
	Smoke Production % x min				
s1	≤ 750				
s2	Not s1				

When tested to BS EN ISO 11925-2:2020 the sample has to have a flame spread (Fs) of: Fs ≤ 150mm within 20 seconds (Class Efl).

#### Results

The test results relate to the behaviour of the test specimens of a material under the particular conditions of test; they are not intended to be the sole criterion for assessing the full potential fire hazard of the materials in use.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 16 May 2022

Our Ref: 25/11166C/04/22 Your Ref:

> Page: 6 of 6

**Client: Jacaranda Carpets** 

### **Results (Continued)**

Specimen No.	<u>Direction of</u> specimen	Smoke O	bscuration % x min	Maximum Flame front (mm)	Critical Heat Flux (kW/m²)	<u>Duration of</u> Flaming (sec)
	<u></u>		<del>201111111</del>	<u>,</u>		<u> </u>
1	Machine	20	11	510	3.8	721
2	Across	20	18	490	4.0	720
3	Machine	22	18	480	4.2	751
4	Machine	23	19	511	3.8	750
Mean of 3 specimens	Machine	22	16	500	3.9	741

<u>Distance</u>	Time for each specimen to burn (s)				
Burnt (mm)	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>	
50	125	126	125	124	
100	130	128	128	127	
150	135	132	132	131	
200	140	144	140	148	
250	155	161	155	160	
300	180	180	175	180	
350	260	240	210	218	
400	330	316	270	300	
450	460	400	390	415	
500	540			520	
550					

#### **Note**

One specimen was initially tested in each direction and whichever direction gave the worst result a further two specimens were tested. Only the results of the 3 specimens in the same direction were used to calculate the mean results.

The specimens of floor covering were tested loose laid over a 6mm fibre cement board, as defined in BS EN 13238:2010.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 16 May 2022

Our Ref: 25/11166C/04/22 Your Ref:

Page: 7 of 6

**Client: Jacaranda Carpets** 

#### Comment

The results meet the requirements of a **Class D**<sub>fl</sub>-s1, as specified in BS EN 13501-1:2018.

An estimation of uncertainty of measurement has been taken into account when making a judgment to any pass/fail criteria. Under our Policy we have used a non-binary decision rule.

See our Decision rules Policy (http://www.bttg.co.uk/decision-rules-policy) for further information.

Reported by: 23 ...... B Marsden (Mrs), Senior laboratory Technician

Countersigned by:..... ..... P Doherty Manager

Enquiries concerning this report should be addressed to Customer Services







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

16 May 2022 Date:

Our Ref: 25/11166C/04/22

Your Ref:

Page: 8 of 6

**Client: Jacaranda Carpets** 

## **Uncertainty Budget - Annex**

The uncertainty budget for BS EN 13501-1:2018 was determined as follows:-

#### BS EN ISO 11925-2:2020

±2 seconds for time recorded removal of flame and terminate test

#### Overall (BS EN ISO 9239-1:2010)

The uncertainty varies, therefore:

a) At position between 0 - 450mm +7% At position between 450mm -1000mm b) +8%

Smoke Obscuration -±15%



