

Confidential Report

Our Ref: 25/11215C1/05/22







Wira House, West Park Ring Road, Leeds, LS16 6QL, UK. Telephone: +44 (0) 113 259 1999

Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 22 June 2022

Our Ref: 25/11215C1/05/22

Your Ref: ---

Page: 1 of 8

Client:	Jacaranda Carpets Limited
Client:	Jacaranda Carpets Limited

1 Cockerel Rise Magnetic Park Desborough Northamptonshire NN14 2WE

JOD LITIE:	Fire Classification	rests on	One Sample of	η Carpet

Clients Order Ref: ---

Date of Receipt: 30 May 2022

Description of Sample: One sample of carpet, referenced; Daiya - handwoven loop 100% wool.

Work Requested: We were asked to make the following test(s):

BS EN 13501-1

- * subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited





Note: This report relates only to the items tested.



Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 22 June 2022

Our Ref: 25/11215C1/05/22 Your Ref:

> Page: 2 of 8

Client: Jacaranda Carpets Limited

FIRE TESTS ACCORDING TO BS EN ISO 11925-2:2020 Reaction to fire tests for building products – Part 2: Ignitability when subjected to direct impingement of flame

Date of Test: 20/06/2022

Conditioning

Test specimens and filter paper conditioned as described in BS EN 13238:2010.

Procedure

The sample was tested in accordance with BS EN ISO 11925-2:2020.

Three specimens from each direction were tested in accordance with the above standard. Specified filter paper was placed beneath the specimen holder and replaced between tests.

The specimens were mounted vertically in the specimen holder so that one end and both sides were enclosed with the exposed end 30mm from the end of the frame. The burner was inclined at an angle of 45°. The flame height was set at 20 mm with the flame impinging on the specimen for 15 seconds on the centre line, 40 mm above the bottom edge.

A marker was placed 150 mm above the upper end of the burner and the time recorded when the flame tip reached the marker, if applicable. The following parameters were also recorded:-

- 1. If ignition occurs
- 2. Presence of flaming debris, if applicable
- Ignition of the filter paper, if applicable 3.

Duration of test

For a flame application time of 15 seconds, the total test duration is 20 seconds after application of the flame.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

22 June 2022 Date:

Our Ref: 25/11215C1/05/22 Your Ref:

> Page: 3 of 8

Jacaranda Carpets Limited

Classification Criteria

Client:

The samples were classified according to BS EN 13501-1:2018 Fire classification of Construction Products and Building Elements: Part 1 - Classification using Test Data from Reaction to Fire Tests, Table 1 - Classes of reaction to fire performance for construction products excluding floorings.

Flaming Classification				
Classification Criteria (mean values)				
E _{FL}	Fs ≤ 150mm within 20 seconds			
F _{FL} Fails Class E _{FL}				
Flaming droplets / particles classification				
Classification Criteria				
No classification	Pass			
d2 Fail (Ignition of paper)				

Results

Specimen			Tip of flame re	eaches 150mm	Flaming droplets	
		Ignition (Yes or No)	Yes or No	Time taken (s)	Yes or No	Ignition of Filter paper (Yes or No)
NA sala in a	1	Yes	No	N/A	No	No
Machine	2	Yes	No	N/A	No	No
Direction	3	Yes	No	N/A	No	No
Across	1	Yes	No	N/A	No	No
Machine	2	Yes	No	N/A	No	No
Direction	3	Yes	No	N/A	No	No

Note

The specimens of floor covering were tested loose laid over a 6mm fibre cement board, as defined in BS EN 13238:2010.

The substrate used was a fibre cement board (ISO 390) with a thickness of (6±1)mm and a density of (1,800±200) Kg/m³ representing the standard substrate of Class A1fl or A2fl.

Test BS EN ISO 11925-2:2020 is accredited under our flexible scope policy.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 22 June 2022

Our Ref: 25/11215C1/05/22

Your Ref:

Page: 4 of 8

Client: Jacaranda Carpets Limited

FIRE TESTS ACCORDING TO BS EN ISO 9239-1:2010

Reaction to fire tests for Floorings - Part 1: Determination of the burning behaviour using a radiant heat source (ISO 9239-1:2010)

Date of Test: 20/06/2022

Conditioning

The specimens were conditioned in accordance with BS EN 13238:2010. The substrate used was a fibre cement board (ISO 390) with a thickness of (6±1)mm and a density of (1,800±200) Kg/m³ representing the standard substrate of Class A1fl or A2fl.

Procedure

The test was carried out in accordance with BS EN ISO 9239-1:2010. The sponsor sampled and cut the specimens to the dimensions stated.

Specimens were individually placed in the combustion chamber and allowed to preheat for two minutes under a radiant panel, which gives an imposed radiant flux ranging from approximately 11.0 kW/m² to 1.0 kW/m² along the specimen.

The pilot flame used was the line burner as described and was applied to the surface of the specimen for 10 minutes and then removed.

The flame front was measured at the end of the test or at 30 minutes if applicable.

Test termination was considered to be when the flame front self extinguished or at 30 minutes, which ever is the sooner.

The heat flux from the panel incident on the specimen when self extinguished or at 30 minutes (critical heat flux CHF or HF-30) was calculated from a prior calibration.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

22 June 2022 Date:

Our Ref: 25/11215C1/05/22 Your Ref:

> Page: 5 of 8

Client: Jacaranda Carpets Limited

Classification Criteria

The samples were classified according to BS EN 13501-1:2018 - Fire classification of Construction Products and Building Elements: Part 1: Classification using Test Data from Reaction to Fire Tests.

For floorings, including their surface coverings the classes are:

Classification	Classification Criteria (mean values) (kW/m²)			
Bfl	8.0			
Cfl	4.5			
Dfl	3.0			
	Smoke Production % x min			
s1	≤ 750			
s2	Not s1			

When tested to BS EN ISO 11925-2:2020 the sample has to have a flame spread (Fs) of: Fs ≤ 150mm within 20 seconds (Class Efl).

Results

The test results relate to the behaviour of the test specimens of a material under the particular conditions of test; they are not intended to be the sole criterion for assessing the full potential fire hazard of the materials in use.







Results (Continued)

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Page:

Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

22 June 2022 Date:

Our Ref: 25/11215C1/05/22 Your Ref:

6 of 8

Jacaranda Carpets Limited

Client:

Specimen No.	<u>Direction of</u> specimen	Smoke Ol Max %	oscuration % x min	Maximum Flame front (mm)	Critical Heat Flux (kW/m²)	<u>Duration of</u> Flaming (sec)
	<u>эрссипси</u>	<u>1410.7.70</u>	70 X 111111	none (mm)	HOX (KVV)III 1	rianning (see)
1	Machine	19	45	230	8.3	780
2	Across	17	39	290	7.2	781
3	Across	16	47	231	8.3	780
4	Across	17	30	260	7.7	740
Mean of 3 specimens	Across	17	39	260	7.7	767

<u>Distance</u>	Time for each specimen to burn (s)			
Burnt (mm)	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>
50	130	129	130	132
100	140	150	145	146
150	158	168	162	160
200	175	190	180	185
250		240		270

Note

One specimen was initially tested in each direction and whichever direction gave the worst result a further two specimens were tested. Only the results of the 3 specimens in the same direction were used to calculate the mean results.

The specimens of floor covering were tested loose laid over a 6mm fibre cement board, as defined in BS EN 13238:2010.







Page:

Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

22 June 2022 Date:

Our Ref: 25/11215C1/05/22 Your Ref:

7 of 8

Client: Jacaranda Carpets Limited

Comment

The results meet the requirements of a possible Class Bfl-s1, but a definite Class C_{fl} -s1, as specified in BS EN 13501-1:2018.

Where required to make a judgement to any pass/fail criteria an estimation of uncertainty of measurement has been taken into account. Under our Policy we have used a non-binary decision rule.

See our decision rules Policy (http://www.bttg.co.uk/decision-rules-policy) for further information.

...... B Marsden (Mrs), Senior laboratory Technician

......P Doherty Manager Countersigned by:....

Enquiries concerning this report should be addressed to Customer Services.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

22 June 2022 Date:

Our Ref: 25/11215C1/05/22

Your Ref:

8 of 8 Page:

Client: Jacaranda Carpets Limited

Uncertainty Budget - Annex

The uncertainty budget for BS EN 13501-1:2018 was determined as follows:-

BS EN ISO 11925-2:2020

±2 seconds for time recorded removal of flame and terminate test

Overall (BS EN ISO 9239-1:2010)

The uncertainty varies, therefore:

At position between 0 – 450mm +7% a) b) At position between 450mm -1000mm +8%

Smoke Obscuration -±15%



