



Confidential Report

Our Ref: 25/05872C2/03/14

Notified Body
for PPE Directive,
Construction Products
Regulation & Marine
Equipment Directive
I.D. No. 0338 & 0339

British Carpet Technical Centre
Wira House, West Park Ring Road,
Leeds, LS16 6QL

Tel No: +44 (0)113 2591999 Fax No: +44 (0)113 2780306



1066

14 April 2014

Our Ref: 25/05872C2/03/14
Your Ref:

Page 1 of 7

Client: Jacaranda Carpets Ltd
1 Cockerel Rise
Magnetic Park
Desborough
Northamptonshire
NN14 2WE

Job Title: **Fire Test on One Sample of Carpet**

Clients Order Ref: --

Date of Receipt: 19 March 2014

Reference: **Santushti**
Description of Sample: Cut and Loop Pile
Textile Backed
Hand Woven Carpet
Measurements: 100cm x 400cm

Work Requested: BCTC were requested to carry out a Fire Test to BS EN 13501-1 on the sample of carpet supplied.



BCTC
CARPET TECHNICAL CENTRE

British Carpet Technical Centre
Wira House
West Park Ring Road
Leeds, LS16 6QL
England

Tel: +44 (0)113 259 1999
Fax: +44 (0)113 278 0306
Web: <http://www.bttg.co.uk>
Email: CSLeeds@bttg.co.uk

14 April 2014

Page 2 of 7

Our Ref: 25/05872C2/03/14
Your Ref:

Jacaranda Carpets Ltd

FIRE TESTS ACCORDING TO BS EN ISO 11925-2:2002 Reaction to fire tests for building products – Part 2: Ignitability when subjected to direct impingement of flame

Date of Test: 14/04/2014

Conditioning

Test specimens and filter paper conditioned as described in BS EN 13238:2001.

Procedure

The sample was tested in accordance with BS EN ISO 11925-2:2002.

Three specimens from each direction were tested in accordance with the above standard. Specified filter paper was placed beneath the specimen holder and replaced between tests.

The specimens were mounted vertically in the specimen holder so that one end and both sides were enclosed with the exposed end 30mm from the end of the frame. The burner was inclined at an angle of 45°. The flame height was set at 20 mm with the flame impinging on the specimen for 15 seconds on the centre line, 40 mm above the bottom edge.

A marker was placed 150 mm above the upper end of the burner and the time recorded when the flame tip reached the marker, if applicable. The following parameters were also recorded:-

1. If ignition occurs
2. Presence of flaming debris, if applicable
3. Ignition of the filter paper, if applicable

Duration of test

For a flame application time of 15 seconds, the total test duration is 20 seconds after application of the flame.





14 April 2014

Page 3 of 7

Our Ref: 25/05872C2/03/14
Your Ref:

Jacaranda Carpets Ltd

Classification Criteria

The samples were classified according to BS EN 13501-1:2002 Fire classification of Construction Products and Building Elements: Part 1 – Classification using Test Data from Reaction to Fire Tests, Table 1 – Classes of reaction to fire performance for construction products excluding floorings.

Flaming Classification	
Classification	Criteria (mean values)
E _{FL}	F _s ≤ 150mm within 20 seconds
F _{FL}	None (No performance determined)

Flaming droplets / particles classification	
Classification	Criteria
No classification	Pass
d2	Fail (Ignition of paper)

Results

Specimen	Ignition (Yes or No)	Tip of flame reaches 150mm		Flaming droplets	
		Yes or No	Time taken (s)	Yes or No	Ignition of Filter paper (Yes or No)
Machine Direction	1	No	No	--	No
	2	No	No	--	No
	3	No	No	--	No
Across Machine Direction	1	No	No	--	No
	2	No	No	--	No
	3	No	No	--	No





BCTC
CARPET TECHNICAL CENTRE

British Carpet Technical Centre
Wira House
West Park Ring Road
Leeds, LS16 6QL
England

Tel: +44 (0)113 259 1999
Fax: +44 (0)113 278 0306
Web: <http://www.btg.co.uk>
Email: CSLeeds@btg.co.uk

14 April 2014

Page 4 of 7

Our Ref: 25/05872C2/03/14
Your Ref:

Jacaranda Carpets Ltd

FIRE TESTS ACCORDING TO BS EN ISO 9239-1:2002 Indicative Reaction to fire tests for Floorings - Part 1: Determination of the burning behaviour using a radiant heat source (ISO 9239-1:2002)

Date of Test: 14/04/2014

Conditioning

The specimen was conditioned in accordance with BS EN 13238:2001. The substrate used was a fibre cement board (ISO 390) with a thickness of (6 ± 1) mm and a density of $(1,800\pm 200)$ Kg/m³ representing the standard substrate of Class A_{1fi} or A_{2fi}.

Procedure

The test was carried out in accordance with BS EN ISO 9239-1. The sponsor sampled and cut the specimen to the dimensions stated.

The specimen was individually placed in the combustion chamber and allowed to preheat for two minutes under a radiant panel, which gives an imposed radiant flux ranging from approximately 11 kW/m² to 1 kW/m² along the specimen.

The pilot flame used was the line burner as described and was applied to the surface of the specimen for 10 minutes and then removed.

The flame front was measured at the end of the test or at 30 minutes if applicable.

Test termination was considered to be when the flame front self extinguished or at 30 minutes, whichever is the sooner.

The heat flux from the panel incident on the specimen when self extinguished or at 30 minutes (critical heat flux CHF or HF-30) was calculated from a prior calibration.





14 April 2014

Page 5 of 7

Our Ref: 25/05872C2/03/14
Your Ref:

Jacaranda Carpets Ltd

Classification Criteria

The sample was classified according to BS EN 13501:2002: Fire classification of Construction Products and Building Elements: Part 1: Classification using Test Data from Reaction to Fire Tests.

For Floorings including their surface coverings the classes are:

Classification	Classification Criteria (mean values) (kW/m ²)
B _{fl}	8.0
C _{fl}	4.5
D _{fl}	3.0
	Smoke Production % x min
s1	≤ 750
s2	Not s1

When tested to BS EN ISO 11925-2:2002 the sample has to have a flame spread (Fs) of: Fs ≤ 150mm within 20 seconds (Class Efl)

Results

The test results relate to the behaviour of the test specimen of a material under the particular conditions of test; they are not intended to be the sole criterion for assessing the full potential fire hazard of the materials in use.





14 April 2014

Page 6 of 7

Our Ref: 25/05872C2/03/14
Your Ref:

Jacaranda Carpets Ltd

Results (continued)

<u>Direction of specimen</u>	<u>Smoke Obscuration</u>		<u>Maximum Flame front (mm)</u>	<u>Critical Heat Flux (kW/m²)</u>	<u>Duration of Flaming (sec)</u>
	<u>Max %</u>	<u>% x min</u>			
Machine	7	40	955	1.2	1800

Distance Burnt (mm)

Time for each specimen to burn (s)

50	131
100	152
150	164
200	191
250	216
300	253
350	300
400	336
450	387
500	442
550	525
600	600
650	720
700	846
750	1034
800	1127
850	1292
900	1500
950	1780

Note

Only one specimen was tested. Results of 3 specimens in the same direction are used to determine an absolute class.

The specimen of floor covering was tested loose laid onto a 6mm fibre cement board as defined in BS EN 13238:2001.





BCTC
CARPET TECHNICAL CENTRE

British Carpet Technical Centre
Wira House
West Park Ring Road
Leeds, LS16 6QL
England

Tel: +44 (0)113 259 1999
Fax: +44 (0)113 278 0306
Web: <http://www.btg.co.uk>
Email: CSLeeds@btg.co.uk

14 April 2014

Page 7 of 7

Our Ref: 25/05872C2/03/14
Your Ref:

Jacaranda Carpets Ltd

Comments


In our opinion, based on the tests carried out on the sample supplied;


- a) the results of the BS EN ISO 11925-2:2002 test indicate the sample meets the requirements of a Class E_{FL}. It should be noted that this is only class that can be achieved when tested to this method alone.
- b) the results of the BS EN ISO 9239-1:2002 test indicate the sample is unclassifiable when tested to this method alone. Therefore, the test was terminated after one specimen.

Conclusion

In our opinion, the results indicate that the sample when classified to BS EN 13501-1:2002 meets an overall classification of: **Class E_{fl}**.

An estimation of uncertainty of measurement has not been taken into account when making a judgement to any pass/fail criteria.

Reported by:.....  B Marsden, Laboratory Technician

Countersigned by:.....  P Doherty, Operational Head

Enquiries concerning this report should be addressed to Customer Services.

